

CHAOS TRADE
Tomasz Pietrzyński
Kolejowa 27
62-010 Pobiedziska
Poland
EU VAT: PL7772785677
tel. +48 665 501 355

Technical data sheet

Item

Product Description: Photoluminescent pigment

Model: M-BL160

Application Scopes

Brush/roller/spray paint indoors/outdoors, screen printing, injection/extrusion/casting plastic, silicone rubber, toys and arts, etc.

Typical chemical properties

Composition: Strontium Aluminate doped with Europium Dysprosium oxides.

Insoluble in organic solvents, water

Decomposition by: Strong acids, strong alkalines, water

Fastness to heat: -40~850C

Typical physical properties

Appearance: yellowish crystal powder

Specific gravity: 3.6g/cm³

Bulk Density: 1.21g/cm³

Particle size distribution: 70-80um

Hardness in Mohs scale: 7,6

Typical luminescent properties

Excitation all visible light and UV light (200~450nm better)

Glow Color: sky-blue

Afterglow Intensity after 10min >160 mcd/m²

60min >20 mcd/m²

600min >1,75 mcd/m²

Afterglow intensity(to 0.32mcd/m²): >2360min under norm DIN67 510

Typical luminance data:

Time	10'	1'	2'	3'	4'	5'	10'	15'	20'	30'	40'	50'	60'	90'	120'	180'	300'	600'
Mcd/m ²	2220	903	568	426	342	287	161	112	84,5	55,6	40,6	31,9	25,6	16,5	12	7,55	4,25	1,91

Lifespan: > 15years under well packing condition.

Safety:Toxic: No

Radioactive: No

Other data:

- Using condition (recommended): With all colorless, transparent medium, such as paint, coating, resin, etc.
- Storage Condition: In cool, dry and ventilated place, with temperature -50~60C
- Packing: 100g, 500g, 1kg, 5kg – PE container; 25kgs /iron pail lined with plastic bags
- Norm Complied: EN71-3, RoHS, DGM, PSPA Class-D, JIS-Z9107 JD, IMO A.752(18), ISO 23601, UL924, ASTM E2030/E2072/E2073, ATPA SS-PS-002-98/SS-PS-004-99, BS 5499-1 2002, NYC Law 26.

Document has been made basing on supplier certificate.