CHAOS TRADE Tomasz Pietrzyński Kolejowa 27 62-010 Pobiedziska Poland EU VAT: PL7772785677 tel. +48 665 501 355

Technical data sheet

Item

Product Description: Photoluminescent pigment

Model: M-PO120

Application Scopes

Brush/roller/spray paint indoors, screen printing, injection/extrusion/casting plastic,

silicone rubber, toys and arts, etc.

Typical chemical properties

Composition: Strontium Aluminate dopped with Europium Dysprosium oxides.

Insoluble in organic solvents, water

Decomposition by: Strong acids, strong alkalines, water

Fastness to heat: -40~230C

Typical physical properities

Appearance: orange-red crystal powder

Specific gravity: 3.6g/cm³ Bulk Density: 1.21g/cm³

Particle size distribution: 30-50um

Hardness in Mohs scale: 7,6

Typical luminescent properties

Excitation all visible light and UV light (200~450nm better)

Glow Color: orange

Afterglow Intensity after 10min >120 mcd/m²

60min >16,8 mcd/m₂ 600min >0,92 mcd/m₂

Afterglow intensity(to 0.32mcd/m₂): >1660min under norm DIN67 510

Typical luminance data:

Time	10"	1'	2'	3'	4'	5'	10'	15'	20'	30'	40'	50'	60'	90'	120'	180'	300'	600'
Mcd/	3676	1145	645,8	447,5	341,2	275,8	138,7	91,19	66,96	42,39	30,37	23,33	18,76	11,5	8,05	4,84	2,52	1,02
m2																		İ

Lifespan: > 15 years under well packing condition.

Safety:Toxic: No Radioactive: No

Other data:

- Using condition (recommended): With all colorless, transparent medium, such as paint, coating, resin, etc.
- Storage Condition: In cool, dry and ventilated place, with temperature -50~60C
- Packing: 100g, 500g, 1kg, 5kg PE container; 25kgs /iron pail lined with plastic bags
- Norm Complied: EN71-3, RoHS, DGM, PSPA Class-D, JIS-Z9107 JD, IMO A.752(18), ISO 23601, UL924, ASTM E2030/E2072/E2073, ATPA SS-PS-002-98/SS-PS-004-99, BS 5499-1 2002, NYC Law 26.

Document has been made basing on supplier certificate.